



Somos® QuickGen 500

Digital light processing (DLP) and
liquid crystal display (LCD) 3D printing



Somos® QuickGen 500 is a fast-printing, general purpose resin for digital light processing 3D printing.

Digital light processing (DLP) 3D printing technology generally boasts faster print speeds and lower capital investment. Combined with **Somos® QuickGen 500**, companies looking to manufacture locally can more quickly and easily adopt 3D printing.

Somos® QuickGen 500 is a fast-printing DLP material with a print speed 2× faster than similar materials. It offers accurate printing for general and functional prototypes.

Somos® QuickGen 500 has unique flexibility; it is more flexible than other resins, but stiffer than elastomers, offering both flexibility and spring back. The material has substantial elongation and a lower modulus with no significant strain rate dependence on elongation at break. This results in consistent performance independent of how quickly force or strain are applied. Many flexible materials show greater influence from the rate of applied force. An economical resin, **Somos® QuickGen 500** can quickly produce high volumes due to its high printing speeds and fast post-processing.

Key Benefits

- Fast printing
- Economical
- Balance of flexibility and stiffness
- Accurate
- Near colorless

Ideal Applications

- General and functional prototypes
- Semi-flexible applications
- Applications with detailed features
- Fluid flow analysis

Preliminary Data

Liquid Properties		Optical Properties		
Appearance	Opaque	E _c	4.85 mJ/cm ²	[critical exposure]
Viscosity	1,375–1,450 cp	D _p	0.160 mm	[slope of cue-depth vs ln (E) curve]
Density	1,093 g/cc	E ₁₀	22 mJ/cm ²	[exposure that gives 0.254 mm (.010 inch) thickness]

385 nm DLP, 5 mW/cm² measured intensity

Layer Thickness (mm)	Time to Cure (s)	Energy to Cure (mJ/cm ²)
0.05	1.5	7.5
0.1	2.44	12.2
0.15	3.8	19
0.2	5.84	29.2

Mechanical Properties*		UV and Thermal Postcure	
ASTM Method	Property Description	Metric	Imperial
D638M	Tensile Modulus	465 MPa	67.4 ksi
D638M	Tensile Strength	20.4 Mpa	3 ksi
D638M	Tensile Elongation at Yield	5%	
D638M	Tensile Elongation at Break	42%	
D638M	Tensile Yield Strength	12 Mpa	1.7 ksi
D790M	Flexural Modulus	408 Mpa	59.2 ksi
D790M	Flexural Yield Stress	15.9 Mpa	2.3 ksi
D790M	Flexural Elongation at Yield	7.7%	
D256	IZOD Impact, Notched	70 J/m	1.3 ft-lb/in
D624	Tear Strength	95 kN/m	542 lb/in
D570-98	Water Absorption	0.57/0.89%	
DMTA	E' (25°C, 37°C)	770/423 Mpa	112/61 ksi

*5 mm/min

Thermal/Electrical Properties		UV and Thermal Postcure	
ASTM Method	Property Description	Metric	Imperial
DMTA	Glass Transition, Tan Delta	62.1°C	143.8°F

These values may vary and depend on individual machine processing and post-curing practices.

[More information at am.covestro.com](https://www.am.covestro.com)



Covestro Deutschland AG
Kaiser-Wilhelm-Allee 60
51373 Leverkusen
Germany

www.covestro.com

The manner in which you use our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, is beyond our control. Therefore, it is imperative that you test our products to determine suitability for your processing and intended uses. Your analysis must at least include testing to determine suitability from a technical, health, safety, and environmental and regulatory standpoint. Such testing has not necessarily been done by Covestro, and Covestro has not obtained any approvals or licenses for a particular use or application of the product, unless explicitly stated otherwise. If the intended use of the product is for the manufacture of a pharmaceutical/medicinal product, medical device¹ or of pre-cursor products for medical devices or for other specifically regulated applications which lead or may lead to a regulatory obligation of Covestro, Covestro must explicitly agree to such application before the sale. Any samples provided by Covestro are for testing purposes only and not for commercial use. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information, including technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed by you that you assume and hereby expressly release and indemnify us and hold us harmless from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent. These values are typical values only. Unless explicitly agreed in written form, they do not constitute a binding material specification or warranted values.

¹Please see the "Guidance on Use of Covestro Products in a Medical Application" document.
Edition: September 2021 · Printed in Germany